

ALKYD BAKING TOP COAT

RANA 753 T

Product information

- 1-Easy application by brush with excellent flow,giving a smooth eggshell appearance.
- 2-Good adhesion to different metallic surface.
- 3-Specially formulated for maintenance work by brush , roller or spray .
- 4-Excellent flexibility.
- 5-High gloss .
- 6- High colour retention .

Physical data

Colour:	customer request
Finish:	gloss
Flash point:	28 [°] c
Volume solids:	44 ±2%
D.f.t:	25-30 microns
Specific gravity:	1.2 ± 0.05gr/cm ³
Theoretical coverage:	18 m ² /lit (at 25 μ d.f.t)
Baking condition:	
Flushing time:	10 minutes
Stoving time:	20 - 30 minutes
Stoving temp. :	140 – 160 [°] c
Component:	1
Application methods:	conventional spray or brush or roller
Recoat intervals:	wet on wet or partially curing
Recommended thinner:	RANA THINN 75
Recommended cleaner:	RANA CLEAN 75
Shelf life:	6 months when stored indoors in unopened Original containers at 5 to 40 [°] c (cool and dry Place).
Curing mechanism:	by solvent release and cure on heat
Substrate:	steel

ALKYD BAKING TOP COAT

RANA 753 T

Typical uses

As a general purpose coating based on alkyd melamin resin on exterior and interior steel work, in mildly to moderately corrosive environment specially in home appliances.

Not suitable for exposure in strong alkaline conditions.

Application information

This RANA CHEM's product is an alkyd melamine paint for industrial uses.

To obtain the maximum performance for which this product is formulated, strict adherence to all application, instructions, precautions, conditions and limitations is necessary.

Application equipment

The following equipment is listed as a guide and suitable equipment from other manufactures may be used.

Adjustments of pressure and change of tip size may be needed to obtain the proper spray characteristics.

1-Conventional spray: industrial equipment with suitable aircap having a fluid tip with a 1.4-1.6mm orifice .

2-Mixer.

3-Brush.

Caution

1-Handle with care.

2-Avoid inhalation of possible solvent vapours or paint mist, as well as paint contact with skin and eyes.

ALKYD BAKING TOP COAT

RANA 753 T

- 3-Apply only in well ventilated areas and ensure that adequate forced ventilation exists when applying paint in confined spaces or when the air is stagnant.
- 4-Always take precautions against the risks of fire and explosions.
- 5-Don't empty into drains and take precautionary measures against static discharges.
- 6-Harmful or fatal if swallowed,immediately seek medical assistance.

Application procedure

- 1-Flush equipment with recommended cleaner before use.
- 2-Stir paint for 5 minutes.
- 3-For spray,thin only as needed for workability.
- 4-Apply a wet coat in even, parallel passes.overlap each pass 50% to avoid bare areas,pinholes or holidays.
- 5-Small damaged or bare areas and random pinholes or holidays can be touched up by brush.
- 6-Clean all equipment with recommended cleaner immediately after use.

Environmental condition

Environmental temperature must be 10-40°C.
Surface temperature must be at least 3°C above dew point to prevent condensation. At freezing temperature surface must be free of ice and relative humidity below 80 %.

Surface preparation

All dirt, grease and other foreign materials ` should be removed with wire brushing , washing with water and detergent and then

RANACHEM

رانا كيمياء فام (سواءى خاص)

ALKYD BAKING TOP COAT

RANA 753 T

phosphatizing or chromating surface .